

General Description:

ACRYLIC 2K SEMIGLOSS BLACK is based on hydroxyl functional acrylic resins and saturated isocyanates with special black pigments. It is weather resistant, unaffected by humidity, heat and sunlight.

Major Uses:

Recommended for outdoor furniture, steel gates, external doors and frames, and automotive refinishes.

Characteristics and Physical Properties:

| | |
|--|---|
| Appearance | Black |
| Specific Gravity (20°C) | 1.10 |
| Viscosity (25°C, FC # 4) | 40 " |
| Flash Point | 20°C |
| Non – Volatile (Wt.%) | 50 |
| Gloss (60°) | 50+/- 5 |
| Application Condition Air Temperature Relative Humidity | 5 ~ 35°C Max. 85% |
| Application Method | Brush, Spray or Roller |
| Recommended Catalyst | Catalyst # 042 |
| Thinner | Thinner # 205/305 |
| Mixing / Dilution Ratio (wt%) (FC # 4 13 ~15 Sec.) | Base : Catalyst : Thinner 100 50 25 ~ 30 |
| Pot Life (20°C) | 5 ~ 6 hrs. |
| Drying Time (20°C) Dust Free To Touch To Recoat Hard | 30 – 35 min. 45 – 60 min. 2 – 3 hrs. 24 – 36 hrs. |
| Coating Rate | 6 - 8 m ² /li |
| Recoating | one coat may be sufficient for ordinary finish however; one additional coat can be applied wet on wet if necessary. Light sanding with 400 ~ 600 mesh sand paper is recommended before subsequent coats, when recoating time exceeds 3 hrs. |

Recommended Under Coat:

Acrylic Primer or Epoxy Basecoat

Application Procedure:

The mixture can be applied by brush, roller or spray. Surface to be painted must be free from dirt and other contaminants. In the remaking of old surface, it is imperative to remove traces of wax, dirt and other foreign matter to ensure a perfect adhesion of paint. Apply 1 – 2 coats of Acrylic or Epoxy Basecoat prior to application of ACRYLIC 2K SEMIGLOSS BLACK

Typical Recommended System:

| | |
|----------------------------|---------|
| Acrylic or Epoxy Basecoat | 2 coats |
| Acrylic Intermediate coat | 2 coats |
| ACRYLIC 2K Semigloss BLACK | 1 coat |

Precautions:

- Paint should be used within the pot life after components have been mixed together.
- Never leave drums of catalyst open.

Storage:

Keep away from heat and fire. Store in the dark, cool and dry places. Shelf life up to 12 months in closed container.

Cleaning of Tools:

All tools should be cleaned with Wash Thinner or Thinner # 305 as soon as possible.

Packing:

Available in 1 USG, 20li Pail, and 200li Drum.

Physiological Hazards:

ACRYLIC 2K SEMIGLOSS BLACK does not contain dangerous solvents, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. ACRYLIC 2K SEMIGLOSS BLACK is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advice.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.

MAS PAINTS & CHEMICAL INDUSTRY

P.O. BOX NO: 23085, SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E

TEL NO: 009716 5311777; FAX: 009716 5311330

Website : <http://www.mas-paints.com>

Email: masuae@emirates.net.ae

