



HYDROTUFF 2K (ANTI BACTERIAL)

General Description:

HYDROTUFF 2K (ANTI BACTERIAL) is a catalyzed water-based polyurethane dispersion for interior/exterior coating. It is developed to provide a hard resistant film with excellent abrasion, good opacity, flow properties, high flexibility and environment-friendly. It contains anti bacterial component suitable for the protection against algal and fungal attack for surface coatings.

Major Uses:

It is best recommended for coating floor surfaces, wooden furniture and the like. It is also widely used for metal application with suitable and compatible primer.

Advantages:

- Excellent hardness
- Flexible
- Non –toxic / environment – friendly.
- Easy to apply
- Fast drying.

Characteristics and Physical Properties:

Appearance	Pigmented
Specific gravity	1.20 kg/L
Viscosity	40+/-5" FC # 4
Gloss	Gloss/Semigloss/Matt
Application condition: Relative humidity Air temperature	85% max. 5 – 35°C
Application method	Brush/Spray
Mixing ratio	10:1
Drying time@25°C Dust free To touch Recoat Piling	20-30' 45-60' 2-3 hrs 24-36 hrs
Storage life	12 months
Coating rate	7-10 m ² /L
Recommended primer Wood Metal	Hydroprime # 100 White Primart /Undercoat Enamel

Application Procedure:

Mix base + hardener with recommended ratio and can be applied by brush or spray.

Surface to be coated must be free from dirt and other contaminants. In the remaking of old woods, it is imperative to remove traces of wax, dirt and other oily matter to ensure a perfect adhesion of paints.

First coat can be diluted with 5-10% with clean demineralised water, and allow to dry for an hour before sanding to remove any raise grain.

Ensure that HYDROTUFF 2K (ANTI BACRTERIAL) is applied uniformly and never leave unsealed surface to avoid moisture.

Storage:

Store in the dark, cool and dry places. Shelf life up to 15 months in closed container.

Chemical Resistance:

HYDROTUFF 2K (ANTI BACTERIAL) has a good resistance without additives. It is resistant to chemical stabilize from Level 1-B DIN 68861 part I. HYDROTUFF 2K (ANTI BACTERIAL) does not contain heavy metal and therefore, it can be use for toys in accordance with European Std'd EN 71-3.

DRYING

The drying room temperature should not be lower than 15°C and the humidity must be less than 85°C.If the condition is beyond the required temperature, the possibility of slow drying smooth film and less chemical resistance. It is recommended for a good dry by force drying w/o humidity starting from normal temperature up to 30°C.

PILING

Due to the thermoplasticity of the water-based resin, the drying during piling is delicate that may result to a different effect. However, force drying plus Catalyst will improve the risk of piling.

Cleaning of Tools:

All tools should be cleaned with water.

Packing:

Available in 1Usg. and 20 liter Pail

Physiological Hazards:



See Safety Indication Sheet.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.

MAS PAINTS & CHEMICAL INDUSTRY

P.O. BOX NO: 23085, SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E

TEL NO: 009716 5311777; FAX: 009716 5311330

Website : <http://www.mas-paints.com>

Email: masuae@emirates.net.ae

