



PU PARQUET SEALER

General Description:

PU PARQUET SEALER is a two component sanding sealer based on plasticising saturated polyester to provide a hard and flexible (even in high thickness application) basecoat for wood especially for parquet and wooden floors.

Major Uses:

Designed to be used as basecoat for semi open pore, high quality furniture and timber window, wood floors, and parquets.

Characteristics and Physical Properties:

Appearance	Opalescent
Specific gravity	0.970 kg/L
Viscosity @ 25°C	29" FC # 4
Flash point	20°C
Non volatile (%wt.)	Base : 43.0 Catalyst: 40.0
Application condition: Air temperature Relative humidity	5~35°C 85% max.
Application method	Brush, Spray, Roller
Recommended Catalyst	Catalyst # 075
Thinner	PU Thinner # 105/205
Mixing ratio	Base:Catalyst:Thinner 100 : 50 : 25-30
Pot life @ 25°C	3 - 4 hrs
Drying time @ 25°C Dust free To touch To recoat Hard Sandable	20 - 25 min. 30 - 45 min. 2 - 3 hrs. 24 - 36 hrs. 1 - 2 hrs.
Coverage	6~8 m ² /L
Recoating interval	Minimum 30 min ~ max 3 hours. Light sanding with 400-600 grit sandpaper is recommended before subsequent coat when recoating exceeds 3 hrs

Precautions:

- Mixing ratio should be correctly observed.
- Paint should be used within the pot life after components have been mixed together. Pot life decreases at higher temperature.
- Bubbling due to 4 ~ 5 coat within relatively short time likely to occur in summer. 1 ~ 2 thin initial coat and longer recoating interval (50 – 60 min) eliminates bubbling.
- Never leave the catalyst open.

Storage:

Keep away from heat and fire. Store in the dark, cool and dry place. Shelf life up to 12 months in closed container.

Cleaning of Tools:

All tools should be cleaned with Wash Thinner or PU Thinner # 105 as soon as possible.

Packing:

Available in 1 Usg, 20lit Pail, and 200lit Drum.

Physiological Hazards:

P.U. PARQUET SEALER does not contain dangerous solvents, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. P.U. PARQUET SEALER is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advise.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.

MAS PAINTS & CHEMICAL INDUSTRY

P.O. BOX NO: 23085, SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E

TEL NO: 009716 5311777; FAX: 009716 5311330

Website : <http://www.mas-paints.com>

Email: masuae@emirates.net.ae

